



# DURA-COAT CHEMICAL 200S

## DESCRIPTION AND RECOMMENDED USES

100% solids, Dura-Coat Chemical 200S is a solvent free, high functionality Novolac Epoxy ceramic filled coating designed particularly as a protective coating for metals in highly aggressive chemical environments especially high wear abrasion. Excellent in a wide array of caustics and acids. Dura-Coat Chemical 200S can be easily applied by brush or roller up to 20 mils without slump.

- It can be applied up to 20 mils without slump
- Suitable for any substrate, steel, bronze, aluminum, concrete
- Suitable for corrosion and abrasion protection

## PACKAGES

	SIZE	REORDER #
OPTIONS	1kg	200S-1
	2kg	200S-2
	7,5kg	200S-7.5
	15kg	200S-15

## APPLICATION AREAS

- Chimneys
- Exhaust gas ducts
- Scrubbers
- Heat exchangers
- Fans and housings
- Valves
- Pump cases
- Tank linings
- Metallic structures
- Impellers
- Many others

## TECHNICAL DATA

Maximum Temperature (dependent on service)	Wet Service	50°C	122°F
	Dry Service	60°C	140°F
Chemical Resistance	Water	Excellent	
	Alkalis	Excellent	
	Inorganic Acids	Excellent	
	Organic Acids	Excellent	
	Organic Solvents	Excellent	
Solids by Volume		100%	
Mixed Density		1.4	
Shore D Durometer Hardness	(ASTM D 2240)	84	
Pot Life		35 min / kg at 72°F	
Vertical SAG Resistance at 21°C (70°F) and 1 mm (40mils)		No sag	
Coverage for 7.5kg Kit	115sf @20mils	10.7m <sup>2</sup> @500 microns	
Mix Ratio	2:1 by weight		Base: Activator
Color	Gray as standard. Blue and red optional. Other colors contact the manufacture		
Shelf Life (unopened containers)	3 years at 55-95°F (13-35°C)		



# DURA-COAT CHEMICAL 200S

## SURFACE PREPARATION

Proper surface preparation is critical to the long-term performance of this product. The exact requirements for surface preparation vary with the severity of the application, expected service life, and the initial substrate conditions. Minimum preparation is mechanical preparation St2/St3. Optimum preparation will provide a surface thoroughly cleaned of all contaminants and roughened to an angular profile between 75-125 µm (3-5 mil). This is normally achieved by initial cleaning and degreasing and then abrasive blasting to a cleanliness of Near White Metal (Sa.21/2), followed by removal of residual abrasive blast residues from the surface to be coated.

## MIXING

Thoroughly mix Activator into Base with mixing stick or drill with low-speed mixing blade scraping sides and bottom of container or mixing board. Mix by weight 1-parts Base to 1-part Activator. Mix thoroughly to produce an even colored and streak-free material. **THINNING:** Never thin.

## CURED TIME

	16°C (60°F)	25°C (77°F)	32°C (90°F)
<b>TACK FREE</b>	6 hours	4 hours	3 hours
<b>LIGHT LOAD</b>	12 hours	8 hours	6 hours
<b>OVERCOAT END</b>	16 hours	10 hours	8 hours
<b>FULL LOAD</b>	24 hours	16 hours	12 hours
<b>FULL CHEMICAL</b>	48 hours	24 hours	18 hours

## APPLICATION

Brush: medium to stiff bristles, of sufficient quality so they do not shed or get stuck in the coating (epoxy-bonded bristles are best). Trim or tape to a length under 1".  
 Roller: use a high-quality roller with 1/8" nap.  
 Airless Spray Gun: 45:1 ratio or higher with TIP 529–535, pressure of 5000 psi or more. Temperature at 50°C (122°F).  
 Plural Component Airless: Graco Xp70 or equivalent, heated to 43°C (109 °F).  
 Robotic Application: Robotic application of the coating on internal circumferential welds using a rotary atomizer.

## APPLICATION TEMPERATURE

Keep between 55 to 95°F (17 to 35°C). Substrate: keep between 45 to 105°F (7 to 40°C). the difference in temperature of the substrate and the material should never exceed 10°F, 5°C. Substrate shall be a minimum of 5°F (3°C) above dew point. Do not apply if relative humidity exceeds 90%. If necessary, heat the metal prior to surface preparation using electric heater or heat lamp. Never use gas, oil, or kerosene heaters as they will leave a greasy residue on metal surface. For best results keep all material in warm area overnight (75°F+) for ease of mixing.

## CLEAN UP

Tools must be immediately cleaned after usage by using industrial alkaline detergent.

## SAFETY

Before using any products, review the appropriate Safety Data Sheet (SDS) or Safety Sheet for your area. Follow standard confined space entry and work procedures, if appropriate.

Manufacturer, Dura-Coat Industrial Inc., makes no warranty either expressed or implied including warranties of merchantability or fitness for a particular purpose for this product. Under no circumstances will the manufacturer be liable for incidental, consequential, or other damages, breach of warranty, strict liability, or any other theory arising out of use of this product. The information and/or recommendations contained herein are based on standard Product and are proprietary and furnished solely for the use of our customers. This information is provided in good faith and believed to be true and accurate as of the date/version of this document. As the manufacturer has no control over the use conditions or application process of the parties using this product, the manufacturer cannot accept responsibility for loss, injury or other damages resulting from the use of the Product or this or any other information provided by the manufacturer. Therefore, no guarantees of any kind, expressed or implied, are made by the manufacturer, Dura-Coat Industrial Inc., regarding this, or any, product manufactured by them or any contracted or licensed manufacturer. DURA-COAT® epoxy products do not provide structural integrity or improvement. They are only used to provide protection from corrosion, wear, abrasion and chemical attack on a given substrate and only to the extent provided for in the Data Sheets, Technical Data Sheets, Safety Data Sheets, and any other information as supplied in writing directly from manufacturers technical support.