




DURA-COAT KRETE-SEAL 800

DESCRIPTION AND RECOMMENDED USES

100% solids, Dura-Coat Krete-Seal 800 is a two component ambient-temperature curing epoxy coating. It is designed particularly as sealing and protection coating for concrete. Its low viscosity allows the Dura-Coat Krete-Seal 800 to flow easily, sealing cracks and filling pits. Dura-Coat Krete-Seal 800 is convenient-to-use, non-sagging easily applied by brush, roll and spray. It is an excellent primer for using with Dura-Coat concrete top coats.

- It is usually applied with 8-10 mils
- Prevent vapors from rising from the substrate
- Suitable for priming concrete with topcoat
- Suitable for immersion and non-immersion service

PACKAGES


	SIZE	REORDER #
OPTIONS	5kg	800-05
	10kg	800-10

APPLICATION AREAS

- Secondary containment
- Chemical tanks
- Concrete walls
- Sumps
- Pump base
- Concrete channels
- Drains
- Chemical processing floors
- Pits
- Neutralization tanks
- Equipment bases

TECHNICAL DATA

Maximum Temperature (dependent on service)	Wet Service	50°C	122°F
	Dry Service	60°C	140°F
Chemical Resistance	Water	Excellent	
	Alkalis	Excellent	
	Inorganic Acids	Good	
	Organic Acids	Good	
	Organic Solvents	Good	
Solids by Volume		100%	
Mixed Density		1.2	
Shore D Durometer Hardness	(ASTM D 2240)	83	
Pot Life		35 min / kg at 72°F	
Vertical SAG Resistance at 21°C (70°F) and 0.25 mm (10mils)		No sag	
Coverage for 10kg Kit	355sf@10mils	33m²@250 micron	
Mix Ratio	2:1 by weight		Base: Activator
Color	Clear amber		
Shelf Life (unopened containers)	3 years at 55-95°F (13-35°C)		



DURA-COAT KRETE-SEAL 800

SURFACE PREPARATION

Proper surface preparation is critically important for the long-term performance of the Dura-Coat Krete-Seal 800. The prepared concrete surface must be structurally sound, free from all contaminants and roughened to an >ICRI CSP 3 profile (similar to #60 grit sandpaper). If a vapor barrier is not present, check for vapor transmission.

SURFACE CLEANING & PROFILING METHODS

- Hydroblasting
- Scarifying
- Steel shot-blasting
- Dry abrasive blasting

CURED TIME

	16°C (60°F)	25°C (77°F)	32°C (90°F)
TACK FREE	4 hours	2 hours	1 hour
LIGHT LOAD	12 hours	6 hours	3 hours
OVERCOAT END	16 hours	10 hours	5 hours
FULL LOAD	24 hours	12 hours	6 hours
FULL CHEMICAL	48 hours	24 hours	12 hours

MIXING

Thoroughly mix Activator into Base with mixing stick or drill with low speed mixing blade scraping sides and bottom of container or mixing board. Mix by weight 1.9-part Base to 1-part Activator. Mix thoroughly to produce an even colored and streak-free material. **THINNING:** Never thin.

APPLICATION

Application temperature range 10°C (50°F)-32°C (90°F) (substrate).
Dura-Coat Krete-Seal 800 may be applied by spray system, brush, or roller.
Brush: medium to stiff bristle of sufficient quality that bristles do not pull out and stick in coating (epoxy glued bristles are best). Trim or tape to <1" nap.
Roller: use good quality 1/8" nap.
To avoid sagging on vertical surfaces the maximum wet film thickness should be between 200 µm-250 µm (8-10 mil) per coat.

CLEAN UP

Tools must be immediately cleaned after usage by using industrial alkaline detergent.

SAFETY

Before using any products, review the appropriate Safety Data Sheet (SDS) or Safety Sheet for your area. Follow standard confined space entry and work procedures, if appropriate.

Manufacturer, Dura-Coat Industrial Inc., makes no warranty either expressed or implied including warranties of merchantability or fitness for a particular purpose for this product. Under no circumstances will the manufacturer be liable for incidental, consequential, or other damages, breach of warranty, strict liability, or any other theory arising out of use of this product. The information and/or recommendations contained herein are based on standard Product and are proprietary and furnished solely for the use of our customers. This information is provided in good faith and believed to be true and accurate as of the date/version of this document. As the manufacturer has no control over the use conditions or application process of the parties using this product, the manufacturer cannot accept responsibility for loss, injury or other damages resulting from the use of the Product or this or any other information provided by the manufacturer. Therefore, no guarantees of any kind, expressed or implied, are made by the manufacturer, Dura-Coat Industrial Inc., regarding this, or any, product manufactured by them or any contracted or licensed manufacturer. DURA-COAT® epoxy products do not provide structural integrity or improvement. They are only used to provide protection from corrosion, wear, abrasion and chemical attack on a given substrate and only to the extent provided for in the Data Sheets, Technical Data Sheets, Safety Data Sheets, and any other information as supplied in writing directly from manufacturers technical support.

