



DURA-COAT MEMBRANE 910

DESCRIPTION AND RECOMMENDED USES

100% solids, Dura-Coat Membrane 910 is a high-elongation hybrid urethane elastomer. It is ideal for tank chimes and is fully compatible with metal, concrete, and other substrates. The elastomer provides high strength and flexibility, while ceramic reinforcement enhances abrasion resistance. Membrane 910 can be easily applied by brush up to 40 mils without sagging.

- Can be applied up to 40 mils without sagging
- Ideal for tank chime protection and sealing
- Suitable for metal and concrete
- Suitable for immersion and non-immersion services

PACKAGES

OPTIONS	SIZE	REORDER #
	1kg	910-01
	2kg	910-02
	7,5kg	910-7.5
	15kg	910-15

APPLICATION AREAS

- Equipment base
- Sealing of ceiling
- Tanks
- Many others
- Pumps exterior
- Tank chime
- Wall Cracks

TECHNICAL DATA

Maximum Temperature (dependent on service)	Wet Service	-30°C	-22°F
	Dry Service	93°C	200°F
Chemical Resistance	Water	Excellent	
	Alkalis	Excellent	
	Inorganic Acids	Excellent	
	Organic Acids	Fair	
	Organic Solvents	Poor	
Elongation		200%	
Specific Gravity		1.4	
Hardness		93 Shore A	
Vertical SAG Resistance at 21°C (70°F) and 1 mm (40mils)		No sag	
Coverage for 1kg Kit	7,5sf@40mils	0.7m ² @1mm	
Mix Ratio	2:1 by weight		Base: Activator
Color	Gray		
Shelf Life (unopened containers)	3 years at 55-95°F (13-35°C)		



DURA-COAT MEMBRANE 910

SURFACE PREPARATION

Proper surface preparation is vitally important to the long-term performance of Dura-Coat Membrane 910. The surface should be clean and rough. Prepare with mechanical cleaning with a rotating wire brush. Clean with solvents (acetone, xylene, alcohol or MEK) and a cloth. No primer is required, Dura-Coat Membrane 910 is applied directly to metal or concrete.

MIXING

Mix the activator well into the base with the mixing rod scraping down the sides and bottom of the container. Mix by weight 2 parts Base with 1 part of Activator. Mix thoroughly to produce a uniform, streak-free material. Never put solvents.

CURED TIME

	16°C (60°F)	25°C (77°F)	32°C (90°F)
TACK FREE	4 hours	2 hours	1 hour
LIGHT LOAD	12 hours	6 hours	3 hours
OVERCOAT END	16 hours	10 hours	5 hours
FULL LOAD	24 hours	12 hours	6 hours
FULL CHEMICAL	48 hours	24 hours	12 hours

APPLICATION

Dura-Coat Membrane 910 can be applied by brush. To avoid sagging on vertical surfaces, the maximum thickness per layer should be up to 1 mm (40 mil) per layer.

CLEAN UP

Tools must be immediately cleaned after usage by using industrial alkaline detergent.

SAFETY

Before using any products, review the appropriate Safety Data Sheet (SDS) or Safety Sheet for your area. Follow standard confined space entry and work procedures, if appropriate.

Manufacturer, Dura-Coat Industrial Inc., makes no warranty either expressed or implied including warranties of merchantability or fitness for a particular purpose for this product. Under no circumstances will the manufacturer be liable for incidental, consequential, or other damages, breach of warranty, strict liability, or any other theory arising out of use of this product. The information and/or recommendations contained herein are based on standard Product and are proprietary and furnished solely for the use of our customers. This information is provided in good faith and believed to be true and accurate as of the date/version of this document. As the manufacturer has no control over the use conditions or application process of the parties using this product, the manufacturer cannot accept responsibility for loss, injury or other damages resulting from the use of the Product or this or any other information provided by the manufacturer. Therefore, no guarantees of any kind, expressed or implied, are made by the manufacturer, Dura-Coat Industrial Inc., regarding this, or any, product manufactured by them or any contracted or licensed manufacturer. DURA-COAT® epoxy products do not provide structural integrity or improvement. They are only used to provide protection from corrosion, wear, abrasion and chemical attack on a given substrate and only to the extent provided for in the Data Sheets, Technical Data Sheets, Safety Data Sheets, and any other information as supplied in writing directly from manufacturers technical support.

